



TECHNICAL DATASHEET

Ti-6AI-7Nb FT 009 – Version 0

The Ti-6Al-7Nb Aluminium – Niobium alpha-beta alloy. Its biocompatibility and mechanical properties are superior to those of the Ti-6Al-4V. This alloy was conceived and developed in 1977 by a team of researchers at Gebruder Sulzer in Winterthur, Switzerland. Their aim was to create a titanium alloy that would meet the demands of the medical and surgical sectors.

APPLICATIONS	ADVANTAGES			
Medical	Biocompatibility Fatigue resistance Corrosion resistance			
STANDARDS	SHAPES			
	BAR			
ASTM F1295 ISO 5832-11 UNS R56700	Diameter 1-45 mm			
	Length 2800-3500 mm			
	Tolerance Ø≤18 mm: h7-h9 – Ø>18 mm: h8-h11			

CHEMICAL COMPOSITION

%	0	Fe	С	Н	Ν	Та	AI	Nb	Ti
min							5.5	6.5	residue
max	0.20	0.25	0.08	0.009	0.05	0.50	6.5	7.5	





Ti-6AI-7Nb FT 009 – Version 0

> MECHANICAL PROPERTIES

Condition	Rm Tensile strength (min MPa)	Rp(Yield st (min I	trength	Elongation New (% min) (%	
Annealed	900	500		10 25	
Sheet and plate					
Dimension thickness (x)	Rm Tensile strength (min MPa)	Rp0.2 Yield strength (min MPa)	4D elongation (% min)		nd test el diameter
	900	800	10	9 T*	
Up to 1.78 mm	888				

> PHYSICAL PROPERTIES

Density (g/cm ³)	4.52	
Hardness (HRc)	30-34	
Modulus of elasticity at 20°C (N/mm ²)	105 x10 ³	
Thermal conductivity at 20°C (W/m °C)	-	3
Mean coefficient of thermal expansion at 20-200°C (mm °C)	-	
Beta transus (°C)	1015	
Fusion temperature (°C)	1650	

The information and technical data contained in this sheet are for information purposes only. Only the information written on our material analysis certificates will be official.

SERVICE CENTERS	Lyon Paris Shanghai Sao Paulo	www.a
-----------------	-------------------------------------	-------